

TEST REPORT: 7191159785-CHM17-CSY

Date: 11 APR 2017

Tel: +65 68851312 Fax: +65 67784301

Client's Ref:

Email: zhou.xiao@tuv-sud-psb.sg

Note: This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.



PSB Singapore

Choose certainty.
Add value.

SUBJECT

Evaluation of "Ultima Protek" Paint Sample as per Green Seal™ GS-11 standard

CLIENT

Asian Paints Nepal Pvt Ltd
P.O.Box 37
Hetauda Industrial District
Hetauda
Nepal

Attn : Om Nath Sinha

DESCRIPTION OF SAMPLE

One exterior emulsion sample labeled as follows was received on 01 Mar 2017.

Product Name	Shade	Quantity
Ultima Protek	UP1	1 Ltr

DATE OF TEST

06 Mar 2017 – 10 Apr 2017



Laboratory:
TÜV SÜD PSB Pte. Ltd.
No.1 Science Park Drive
Singapore 118221

Phone : +65-6885 1333
Fax : +65-6776 8670
E-mail: enquiries@tuv-sud-psb.sg
www.tuv-sud-psb.sg
Co. Reg : 199002667R

Regional Head Office:
TÜV SÜD Asia Pacific Pte. Ltd.
1 Science Park Drive, #02-01
Singapore 118221
TÜV®

TEST REPORT: 7191159785-CHM17-CSY
11 APR 2017



PSB Singapore

METHOD OF TEST

Sample was tested for the following tests.

Test	Method
1) Carcinogens, Mutagens, and Reproductive Toxins	By Gas Chromatograph –Mass Spectrometry (GC-MS) Screening method.
2) Volatile organic compound content	By BS EN ISO 11890-2:2013, Paints and varnishes – <i>Determination of volatile organic compound (VOC) content – Part 2 : Gas-chromatographic method.</i>
3) Formaldehyde	The sample was analysed by UV-Vis Spectrophotometer using Acetylacetone as reagent.
4) Volatile Aromatic Hydrocarbons	By Headspace Gas Chromatograph - Mass Spectrometry (HS-GC-MS).
5) Mercury, Lead, Cadmium and Antimony	The sample was digested in inorganic acid, followed by analysis using Inductively Coupled Plasma Atomic Emission Spectroscopy (ICP-AES).
6) Hexavalent Chromium	The sample was analysed by UV-Vis spectrometer using 1,5-Diphenylcarbohydrazide as derivatizing agent.
7) Hazardous air pollutants and Ozone-depleting compounds	By Headspace Gas Chromatograph - Mass Spectrometry (HS-GC-MS).
8) Phthalates (DEHP, BBP, DBP, DnOP, DEP, DMP)	By Gas Chromatograph –Mass Spectrometry (GC-MS).
9) 1,2-dichlorobenzene	By Gas Chromatography with Flame Ionization Detector (GC-FID)
10) Triphenyl tins and tributyl tins	By Gas Chromatograph –Mass Spectrometry (GC-MS).
11) Triclosan	By Gas Chromatograph –Mass Spectrometry (GC-MS).
12) Alkyl Phenol Ethoxylates	BS3762 : 1990 Analysis of formulated Detergent

SUMMARY OF TEST RESULTS

The summary of test results for “Ultima Protek”.

Item No.	Test	Result	Method Detection Limit	GS 11 Criteria	Inferred Remark
1	Carcinogens, Mutagens, and Reproductive Toxins	Not Detected	1000 ppm	Not Detected	Pass
2	Hazardous air pollutants and Ozone-depleting compounds	Not Detected	1000 ppm	Not Detected	Pass
3	VOC Content	11.8 g/L	2 g/L	< 100 g/L*	Pass
4	Free Formaldehyde Content	10.7 ppm	10 ppm	No Formaldehyde donors, free < 100 ppm	Pass
5	Volatile Aromatic Hydrocarbons	Not Detected	100 ppm	≤ 0.5% (w/w)	Pass
6	Heavy Metals: Mercury, Lead, Cadmium, Chromium, Antimony	Not Detected	1 ppm	Not Detected	Pass
7	Hexavalent Chromium	Not Detected	100 ppm	Not Detected	Pass
8	Phthalates	Not Detected	10 ppm	Not Detected	Pass
9	1,2-dichlorobenzene	Not Detected	10 ppm	Not Detected	Pass
10	Triphenyl tins and tributyl tins	Not Detected	10 ppm	Not Detected	Pass
11	Triclosan	Not Detected	100 ppm	Not Detected	Pass
12	Alkyl Phenol Ethoxylates	Not Detected	100 ppm	Not Detected	Pass

* VOC content limits set by CARB (i.e. Flat coatings < 50 g/L; Non-Flat coatings < 100 g/L; Floor coatings < 100 g/L etc.)

RESULTS (Cont'd)

Table 1: The Screening test results for "Ultima Protek".

Test	Result	Method Detection Limit
Carcinogens, Mutagens, and Reproductive Toxins	Not Detected	1000 ppm

Table 2: The Volatile Organic Compound (VOC) content for "Ultima Protek".

Test	Result	Method Detection Limit
VOC Content ^a	11.8 g/L ^b	2 g/L

a) Volatile organic compound (VOC) means any organic compound having an initial boiling point less than or equal to 250°C measured at a standard pressure of 101,3kPa.

b) The result was calculated based on the specific gravity = 1.33 provided by the client

Table 3: The Formaldehyde results for "Ultima Protek".

Test	Result	Method Detection Limit
Free Formaldehyde Content ^c	10.7 ppm	10 ppm

c) GS-11 Criteria prohibited Formaldehyde donor as ingredient, product free formaldehyde content for green product limit < 100 ppm.

Table 5: The Elemental results for "Ultima Protek"

Test	Result	Method Detection Limit
Mercury	Not Detected	1 ppm
Lead	Not Detected	1 ppm
Cadmium	Not Detected	1 ppm
Antimony	Not Detected	1 ppm
Hexavalent Chromium	Not Detected	100 ppm

Table 6: The analytical results of prohibited substances for "Ultima Protek".

Test	Result	Method Detection Limit
Hazardous air pollutants	Not Detected	1000 ppm
Ozone-depleting compounds	Not Detected	1000 ppm
Volatile Aromatic Hydrocarbons	Not Detected	100 ppm
Phthalates (DEHP, BBP, DBP, DnOP, DEP, DMP)	Not Detected	10 ppm
1,2-dichlorobenzene	Not Detected	10 ppm
Triphenyl tins and tributyl tins	Not Detected	10 ppm
Triclosan	Not Detected	100 ppm
Alkyl Phenol Ethoxylates	Not Detected	100 ppm



MS CHOO SEOW YAH
TECHNICAL EXECUTIVE



DR XIAO ZHOU
PRODUCT MANAGER
MICROCONTAMINATION DIAGNOSIS
CHEMICAL & MATERIALS

TEST REPORT: 7191159785-CHM17-CSY

11 APR 2017



PSB Singapore

Please note that this Report is issued under the following terms :

1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
2. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
5. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.

July 2011

