



METHOD OF TEST

CPSC-CH-E1003-09.1

Standard Operating Procedure for Determining Lead (Pb) in Paint and Other Similar Surface Coatings

RESULTS

Sample Reference	Lead (as Pb), %wt/wt	Lead (as Pb), ppm by weight	Specification, %wt/wt
Black	0.005	50	0.009 max
Chocolate	0.005	50	0.009 max
Leaf Brown	0.007	70	0.009 max
Golden Yellow	0.008	80	0.009 max
Phirozi	0.008	80	0.009 max
Bus Green	0.002	20	0.009 max
P.O. Red	0.004	40	0.009 max

DULIN CHRISTIAN BRYAN
CHEMIST

for DR LI SIHAI
AVP / SENIOR CHEMIST
COATINGS & INDUSTRIAL CHEMICALS
CHEMICAL & MATERIALS